

Pipeline Steel welding electrodes

AK-657GX is a low-alloy high-strength steel electrode with low-hydrogen sodium type coating for X80 pipeline. It adopts DC reverse connection and can perform all-position welding.

3.2mm	Lot No.: AD4	Date: Jul.10.2024		
AK E657GX	EN ISO	AWS A5.5	Certificate number	
Welding electrodes		E9015-G	2407-1006	

CHEMICAL COMPOSITION OF WIRE (%)

	С	Si	Mn	S	Р	Ni	Cr	Мо	Cu	
%	0.079	0.38	1.86	0.013	0.018	0.28	0.19	0.35	0.01	

THE TESTRESULTS OF MECHANICAL PROPERTY OF DEPOSITED METAL

	Impact test				
Tensile Strength(Mpa)	Yield Point (Mpa)	Elongation (%)	Temp (OC)	Impact Value(J)	
640	530	27	-20	128/130/131	

Bend test—Face	Bend test—Side	Redrying	X Reys Test	Dictonary flux	HRC	HD
ОК	ОК	ОК				

 2.5mm(3/32″)	3.2mm(1/8″)	4.0mm(5/32″)	
 350mm	350mm	350mm	

NOTICE: The results reported are based upon testing of the product under controlled laboratory conditions in accordance with American Welding Society Standards. Actual use of the product may produce different results due to varying conditions. An example of such conditions would be electrode size, plate chemistry, environment, weldment design, fabrication methods, welding procedure and service requirements. Thus the results are not guarantees for the use in the field. The manufacturer disclaims any warranty of merchantability of fitness for any particular purpose with respect to its products.

CAUTION: Consumers should be thoroughly familiar with the safety precautions on the warning label posted in each shipment and in the American National Standards A49.1, "Safety in Welding and Cutting," published by the American Welding Society, 550 NW LeJune Road, Miami, FL 33126: OSHA Safety and Health Standards 29 CRF 1910 is available from the U.S. Department of Labor, Washington, D.C. 20210.